

Elite Sand Finish Elite Coarse Sand

Elite Rough Trowel Elite Create-A-Finish



DESCRIPTION:

- 100 percent acrylic-based elastomeric textured finish
- DPR (Dirt Pick-up Resistance) chemistry
- Highly flexible: can bridge existing hairline cracks
- Integrally colored with high quality pigments

USES:

Finishing coat for:

- FRP Concentrate and FRP Sanded
- New or existing stucco and concrete surfaces
- Renovation of old stucco and concrete walls
- Finishing of masonry walls in combination with either Flex or Prime-A-Flex Base Coat as leveler

COMPOSITION:

- Binder base: 100 percent acrylic polymer with surface-hardening property
- Aggregate: Pure crushed marble, rust-free
- Water base: VOC-Compliant
- Pigment base: Titanium dioxide
- Color: Surewall standard colors or tinted to desired custom color

TESTING:

- Environmental Durability: Passes ASTM G 23 resistance to accelerated weathering and ultraviolet test
- Resistance to wind-driven rain: (TT-C-555B): passes
- Mildew Testing: (ASTM D3273): No growth
- Vapor Permeability: (ASTM E96): greater than 10 Perms. Water-vapor permeable; does not create a vapor barrier

100% Acrylic

DPR

Elite Sand Finish Elite Coarse Sand

Elite Rough Trowel Elite Create-A-Finish

COVERAGE:

Depending on the condition of the substrate and method of application, approximate coverages are:

Surewall Elite Sand Finish
Aggregate size: 1.0mm
150 - 165 sq. ft. (14 - 15 m²)/pail

Surewall Elite Coarse Sand
Aggregate size: 1.5mm
120 - 135 sq. ft. (11 - 12.5 m²)/pail

Surewall Elite Rough Trowel
Aggregate size: 1.5mm
120 - 135 sq. ft. (11 - 12.5 m²)/pail

Surewall Elite Create-A-Finish
60 - 150 sq. ft. (6 - 14 m²)/pail
depending on texture

CONTAINER:

65 lbs. (29.5 kg) net weight in plastic pails.

- Storage: Protect from sun and freezing at all times
 - Do not stack pails more than 3 pails high
- Shelf Life: One year if protected from sun and frost

DRYING TIME:

48 hours under normal conditions. High humidity and low temperatures extend drying time.

CLEANUP:

Water soluble prior to drying. Clean tools and containers with water prior to drying.

SURFACE PREPARATION:

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days.
- Check concrete surfaces for alkalinity and treat. Any form-release agents or bond breakers must be removed.
- Uneven concrete or masonry can be leveled with either Flex or Prime-A-Flex Base Coat or other suitable, compatible product.
- For interior drywall, prepare as for painting.
- Prime with Surewall Pre-Coat Acrylic Primer.
- For application of Surewall Pre-Coat Acrylic Primer, refer to the Product Data Sheet.
- For additional options, contact Surewall Technical Services Department.

MIXING:

- Use clean equipment for mixing and preparation
- Stir to obtain a homogeneous consistency using a heavy-duty 1/2 in. (13mm) drill with a rust-free paddle at 400-500 r/min. Avoid air entrainment.
- A small amount of clean, potable water may be added to aid workability. Do not exceed 8 oz. (.24 L) per full pail of finish. To avoid color and texture variations, add the same amount of water to each pail of finish.

APPLICATION:

- Read the entire label before using this product
- Always maintain a wet edge and work to corners or joints. For best color consistency, use finish with the same batch number within a wall section. Keep container closed when not in use.
- Application: use a clean stainless steel trowel and apply a uniform coat the thickness of the largest aggregate size of the finish.
- Texturing: use a clean plastic float or stainless steel trowel, wipe frequently. Apply moderate pressure with consistent motion, rolling the large aggregates to obtain the desired texture.

LIMITATIONS:

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, unpainted and free from any residue which may affect the ability of the finish to bond to the surface.
- Avoid application in direct sunlight in hot weather.
- Due to the composition of this product, minor pin holes may be noticeable in the cured finish.